

UDC 669.14.018.29.018.62-122.4-153.65-4:620.1

April 1993

Hot rolled products made from weldable,
fine grain structural steel
Technical delivery conditions for normalized rolled steel
English version of DIN EN 10 113 Part 2

DIN
EN 10 113
Part 2

Warmgewalzte Erzeugnisse aus schweißgeeigneten Feinkornbaustählen;
Lieferbedingungen für normalgeglühte/normalisierend gewalzte Stähle

This standard, together
with the April 1993
editions of DIN EN 10 028
Parts 1 and 3 and
DIN EN 10 113 Part 1,
supersedes DIN 17 102,
October 1983 edition.

European Standard EN 10 113-2: 1993 has the status of a DIN Standard.

A comma is used as the decimal marker.

National foreword

This standard has been prepared by ECISS/TC 10.

The responsible German body involved in its preparation was the *Normenausschuß Eisen und Stahl* (Steel and Iron Standards Committee), Technical Committee *Stähle für den Stahlbau*.

DIN EN 10 113 is divided into three Parts. Part 1 specifies general technical delivery conditions for hot rolled products made from weldable fine grain steel. The present standard gives more specific requirements for such steel in the normalized condition, and Part 3, for thermomechanically rolled steel.

Standards referred to

(and not included in **Normative references**)

- DIN EN 10 028 Part 3 Flat products made from steel for pressure purposes; weldable, normalized, fine grain steels
DIN EN 10 113 Part 1 Hot rolled products made from weldable, fine grain structural steel; general technical delivery conditions
DIN EN 10 113 Part 3 Hot rolled products made from weldable, fine grain structural steel; technical delivery conditions for thermomechanically rolled steel

Previous edition

DIN 17 102: 10.83.

Amendments

In comparison with the October 1983 edition of DIN 17 102, the following amendments have been made.

- a) The field of application is now limited to structural steel.
- b) Specifications for normalized products have been split up between Parts 1 and 2.
- c) The steel grades with a minimum yield strength of 255, 285, 315, 380 and 500 N/mm² are no longer included; that with 275 N/mm² is included for the first time.
- d) Some of the specifications made for chemical composition and mechanical properties have been changed.
- e) The steel designations and material numbers have been changed.

International Patent Classification

C 21 D 001/00
B 22 D 011/06
G 01 B 021/02
G 01 N 033/20

Continued overleaf.
EN comprises 6 pages.

Editor's note

*This standard reproduces the official text of the English version of EN 10 113-2 as issued by CEN. In its preparation for publication as DIN EN 10 113 Part 2 (English version), certain points have been noted which we consider to be in need of correction. These have been marked *). The suggested amendments are given below and will be forwarded to the responsible CEN Secretariat for its consideration.*

In presentation, orthography, punctuation and hyphenation, the aim has been to implement the PNE Rules consistently. Obvious errors (e.g. redundancies and omissions) have been rectified without further reference.

Suggested amendments

- 1 For the sake of clarity, clause 1 should be amended to read: 'This European Standard, in conjunction with Part 1, specifies technical delivery conditions for flat and long products made from hot rolled, weldable, fine grain structural steel supplied in the normalized condition (specifically, steel grades S275, S355, S420 and S460). Table 1 specifies the chemical composition of such steel, and tables 3, 4 and 5 specify their mechanical properties. Products made from steel grades S275, S355 or S420 are supplied in nominal thicknesses ≤ 150 mm, and from S460, in nominal thicknesses ≤ 100 mm. The option numbers given in various subclauses refer to the optional requirements defined in Part 1 of this European Standard.'
- 2 The last sentence of subclause 4.2 does not reflect the German text, which translates: 'In the event ... options, the material shall be supplied in accordance with the general requirements specified here.'
- 3 For the purpose of elaboration, the example given in subclause 6.2 should be amended to read: 'Steel (S) in the normalized condition (N) in compliance with this standard, with a specified minimum yield strength at ambient temperature of 355 N/mm² (355) and a specified minimum value of impact energy at -50°C (L) shall be designated ...'.
- 4 The heading of subclause 7.5.2.2.1 does not reflect the German text, which translates as 'Suitability for cold bending, chamfering and cold flanging'. Likewise, the term 'flanging' as used in the text to that subclause should be replaced by the above terms.
- 5 To avoid confusion, the heading of subclause 8.2 should read: 'Test batch', and the text: 'The test batch shall be in accordance with EN 10 113-1.'
- 6 For the sake of comprehension, the first paragraph of subclause 8.3.2 should be amended to read: 'It may be specified at the time of ordering that the parent plate or coil for flat products either be tested for impact energy only, or be tested for both impact energy and tensile strength.'

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 10113-2

March 1993

UDC 669.14.018.29.018.62-122.4-153.65-4:620.1

Descriptors: Iron and steel products, hot rolled products, structural steels, welded construction, delivery conditions, designation, quality classes, chemical composition, grades, quality, mechanical properties, inspection, tests.

English version

Hot-rolled products in weldable,
fine grain structural steels

Part 2: Delivery conditions for normalized/normalized rolled steels

Produits laminés à chaud en aciers de construction soudable à grains fins.
Partie 2: Conditions de livraison des aciers à l'état normalisé/laminage normalisé

Warmgewalzte Erzeugnisse aus schweißgeeigneten Feinkornbaustählen.
Teil 2: Lieferbedingungen für normalgeglühte/normalisierend gewalzte Stähle

This European Standard was approved by CEN on 1993-03-05.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart 36, B-1050 Brussels

Contents

	Page		Page
Foreword	2	7.5 Technological prope ^r ts	3
1 Scope	2	7.6 Surface condition	3
2 Normative references	2	7.7 Internal defects	3
3 Definitions	2	8 Testing and inspection	3
4 Information to be supplied by the purchaser	2	8.1 General	3
4.1 General	2	8.2 Sampling ⁺)	3
4.2 Options	2	8.3 Test unit	3
5 Dimensions, tolerances and mass	2	8.4 Determination of chemical composition	4
5.1 Dimensions and tolerances	2	8.5 Mechanical tests	4
5.2 Mass	2	8.6 Test methods	4
6 Classification into grades and designation	2	8.7 Retests and resubmission for testing	4
6.1 Classification into grades	2	8.8 Inspection documents	4
6.2 Designation	3	9 Marking	4
7 Technical requirements	3	10 Complaints	4
7.1 Steelmaking process	3	11 Options	4
7.2 As delivered condition	3	11.1 All products	4
7.3 Chemical composition	3	11.2 Flat products	4
7.4 Mechanical properties	3	11.3 Long products	4

Foreword

This European Standard has been drawn up by ECISS/TC 10 'Structural steel; quality standards', the Secretariat of which is held by NNI.

This European Standard replaces EURONORM 113-72 'Special quality weldable structural steel grades and quality; general provisions'.

Technical Committee ECISS/TC 10 met in June 1991 in Brussels and agreed to submit the text to Formal Vote. The result was positive. The following countries were represented at that meeting: Austria, Belgium, Denmark, Finland, France, Germany, Italy, Luxembourg, Netherlands, Spain, Sweden and UK.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, and conflicting national standards withdrawn, by September 1993 at the latest.

In accordance with the CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

Part 2 of this European Standard, in addition to Part 1, specifies requirements for flat and long products of hot-rolled weldable fine grain structural steel in the normalized delivery condition in the grades and qualities given in table 1 (chemical composition) and tables 3, 4 and 5 (mechanical properties), in thickness ≤ 150 mm for grades S275, S355 and S420 and in thickness ≤ 100 mm for grade S460.*)

2 Normative references

The normative references listed in EN 10 113-1 shall apply.

3 Definitions

The definitions given in EN 10 113-1 shall apply.

4 Information to be supplied by the purchaser

4.1 General

The following information shall be supplied by the purchaser at the time of ordering:

- a) details of the product form and relevant quantities;
- b) reference to this European Standard;
- c) nominal dimensions and tolerances (see 5.1);
- d) the grade and quality of the steel (see tables 1 to 5);
- e) the type of inspection document (see 8.8).

Where no such specifications are made, the supplier shall consult with the purchaser.

4.2 Options

A number of options is specified in clause 11. In the event that the purchaser does not indicate his wish to implement any of these options, the supplier shall supply in accordance with the basic specification.*)

5 Dimensions, tolerances and mass

5.1 Dimensions and tolerances

The dimensions and tolerances shall be in accordance with the relevant European Standards and EURONORMS (see 2.2 of EN 10 113-1).

5.2 Mass

The mass of steel shall comply with EN 10 113-1.

6 Classification into grades and designation

6.1 Classification into grades

Steel grades S275 and S355 are classified as unalloyed quality steels, and steel grades S420 and S460, as alloy special steels, in EN 10020.

6.2 Designation

The designation shall be in accordance with EN 10 113-1.

EXAMPLE:

Normalized steel with a specified minimum yield strength at ambient temperature of 355 N/mm², and with a specified minimum impact value at -50 °C:*)

Steel EN 10 113-2 - S355NL

7 Technical requirements

7.1 Steelmaking process

The steelmaking process shall be in accordance with EN 10 113-1.

Option 1.

7.2 As delivered condition

The products shall be supplied in the normalized condition, or in an equivalent condition obtained by normalizing rolling, as defined in clause 3.

7.3 Chemical composition

7.3.1 The chemical composition, as determined by ladle analysis, shall comply with the values specified in table 1.

7.3.2 Table 1 of EN 10 113-1 shall apply for the limit deviations for the product analysis from the limiting values specified for the ladle analysis. The manufacturer shall, at the time of ordering, inform the purchaser of any alloying elements which will be deliberately added to the material to be supplied.

7.3.3 If agreed at the time of ordering, a maximum value of carbon equivalent (CEV), in accordance with table 2, shall apply.

Option 2.

7.4 Mechanical properties

7.4.1 General

When tested in accordance with clause 8, either in the as delivered condition specified in 7.2 or after normalizing after delivery, the values of mechanical properties shall be as specified in tables 3 and 4.

7.4.2 Impact energy

Determination of impact energy shall be carried out in accordance with EN 10 113-1.

Option 4.

Option 5.

7.5 Technological properties

7.5.1 Weldability

Weldability shall be in accordance with EN 10 113-1.

7.5.2 Formability

NOTE: Recommendations regarding hot and cold forming are laid down in EU IC 2.

7.5.2.1 Hot forming

Where hot forming is to be carried out after delivery (see 7.4.1), the products shall comply with tables 3 and 4.

7.5.2.2 Cold forming

7.5.2.2.1 Flangeability*)

If specified at the time of ordering, plate, sheet, strip and wide flats with a nominal thickness ≤ 16 mm shall be suitable for flanging,*) without cracking, with the following minimum bend radii:

- twice the nominal thickness with the bend axis in the transverse direction, and 2,5 times the nominal thickness with the bend axis in the longitudinal direction, for steel grades S275 and S355;
- four times the nominal thickness with the bend axis in the transverse direction, and five times the nominal thickness with the bend axis in the longitudinal direction, for steel grades S420 and S460.

Option 11.

7.5.2.2.2 Roll forming

If specified at the time of ordering, plate and strip with a nominal thickness ≤ 8 mm shall be suitable for the production of sections by means of cold forming (e.g. in accordance with EURONORM 162), with the minimum bend radii specified in 7.5.2.2.1.

Option 12.

NOTE: Steel grades that are suitable for roll forming are also suitable for the production of cold formed square and rectangular hollow sections.

7.5.3 Other requirements

7.5.3.1 If specified at the time of ordering, grades S275 and S355 shall be suitable for hot-dip galvanizing and shall comply with the relevant product quality requirements.

Option 7.

7.5.3.2 If agreed at the time of ordering, heavy sections shall be suitable for slitting.

Option 15.

7.6 Surface condition

The surface condition shall be in accordance with EN 10 113-1.

Option 8.

7.7 Internal defects

The specifications given in EN 10 113-1 regarding internal defects shall be complied with.

Option 13 (for flat products).

Option 16 (for long products).

8 Testing and inspection

8.1 General

The specifications of 8.1 of EN 10 113-1 shall be complied with.

Option 9.

8.2 Sampling*)

Sampling shall be in accordance with EN 10 113-1.*)

8.3 Test unit

8.3.1 A test unit shall consist of products of the same form and grade and be within the same thickness range specified in table 3.

For verifying the mechanical properties, the test unit shall have a mass of 40 t or less.

Page 4
EN 10 113-2:1993

8.3.2 If specified at the time of ordering, for flat products the impact test only or the impact test and the tensile test shall be carried out on each parent plate or coil.*)

Options 19a and 19b.

8.4 Determination of chemical composition

Determination of the chemical composition shall be in accordance with EN 10 113-1.

Option 3.

8.5 Mechanical tests

The requirements for mechanical tests specified in EN 10 113-1 shall be complied with.

8.6 Test methods

The test methods specified in EN 10 113-1 shall be complied with.

8.7 Retests and resubmission for testing

The requirements for retests and resubmission for testing specified in EN 10 113-1 shall be complied with.

8.8 Inspection documents

The requirements for inspection documents specified in EN 10 113-1 shall be complied with.

9 Marking

The marking of flat and long products shall be as specified in EN 10 113-1.

Option 10.

10 Complaints

The specifications regarding complaints given in EN 10 113-1 shall apply.

11 Options

11.1 All products

See options 1 to 10 in EN 10 113-1.

17) Whether values of mechanical properties are to be specified for grade S460 in thicknesses > 100 mm or for grades S275, S355 or S420 in thicknesses > 150 mm (see tables 3, 4 and 5).

18) Whether a maximum S content of 0,007 % is required for products having a thickness ≤ 16 mm (see table 1), intended to be used in railway applications.

11.2 Flat products

See options 11 to 14 in EN 10 113-1.

19a) Whether impact testing only is to be carried out on each parent plate or coil (see 8.3.2).

19b) Whether both impact testing and tensile testing are to be carried out on each parent plate or coil (see 8.3.2).

11.3 Long products

See options 15 and 16 in EN 10 113-1.

Table 1: Steel grades and their chemical composition as determined by ladle analysis

Designation		Percentage by mass													
Symbol as in EN 10027-1 and ECIS IC 10	Material number as in EN 10027-2	C	Si	Mn	P	S	Nb	V	Al _{total}	Ti	Cr	Ni	Mo	Cu	N
		max.	max.		max.	max. ¹⁾	max.	max.	min. ²⁾					max.	
S275N	1.0490	0,18	0,40	0,50 to 1,40	0,035	0,030	0,05	0,05	0,02	0,03	0,30	0,30	0,10	0,35	0,015
S275NL	1.0491	0,16			0,030	0,025									
S355N	1.0545	0,20	0,50	0,90 to 1,65	0,035	0,030	0,05	0,12	0,02	0,03	0,30	0,50	0,10	0,35	0,015
S355NL	1.0546	0,18			0,030	0,025									
S420N	1.8902	0,20	0,60	1,00 to 1,70	0,035	0,030	0,05	0,20	0,02	0,03	0,30	0,80	0,10	0,70 ³⁾	0,025
S420NL	1.8912				0,030	0,025									
S460N	1.8901	0,20	0,60	1,00 to 1,70	0,035	0,030	0,05	0,20	0,02	0,03	0,30	0,80	0,10	0,70 ³⁾	0,025
S460NL	1.8903				0,030	0,025									

1) For railway applications, a maximum S content of 0,007 % may be agreed at the time of ordering, for all products with a thickness ≤ 16 mm.
Option 18.

2) If sufficient nitrogen-binding elements are present, the minimum total Al content need not apply.

3) If the Cu content is greater than 0,35 %, then the Ni content shall be at least half the Cu content.

Table 2: Maximum carbon equivalent based on ladle analysis
(if agreed at the time of ordering)
Option 2

Designation		Maximum carbon equivalent, in %, for a nominal product thickness, in mm, of		
Symbol as in EN 10 027-1 and ECIS IC 10	Material number as in EN 10 027-2	≤63	> 63 ≤100	> 100 ≤150
		S275N S275NL	1.0490 1.0491	0,40
S355N S355NL	1.0545 1.0546	0,43	0,45	0,45
S420N S420NL	1.8902 1.8912	0,48	0,50	0,52
S460N ¹⁾ S460NL ¹⁾	1.8901 1.8903	—	—	—

¹⁾ If agreed at the time of ordering, the following shall apply:
V + Nb + Ti ≤ 0,22 % and Mo + Cr ≤ 0,30 %.

Table 3: Mechanical properties at ambient temperature for normalized steel

Designation		Mechanical properties ¹⁾								Elongation at fracture ²⁾ ($L_0 = 5,65\sqrt{S_0}$) % min.
		Tensile strength, R_m , for a nominal product thickness, in mm, of		Upper yield strength, R_{eH} , for a nominal product thickness, in mm, of						
		≤100	> 100 ≤150	≤16	> 16 ≤40	> 40 ≤63	> 63 ≤80	> 80 ≤100	> 100 ≤150	
S275N S275NL	1.0490 1.0491	370 to 510	350 to 480	275	265	255	245	235	225	24
S355N S355NL	1.0545 1.0546	470 to 630	450 to 600	355	345	335	325	315	295	22
S420N S420NL	1.8902 1.8912	520 to 680	500 to 650	420	400	390	370	360	340	19
S460N S460NL	1.8901 1.8903	550 to 720	—	460	440	430	410	400	—	17

¹⁾ For thicknesses > 100 mm for grade S460 and for thicknesses > 150 mm for grades S275, S355 and S420, the values shall be the subject of agreement at the time of ordering.
Option 17.

²⁾ For product thicknesses < 3 mm for which test pieces with an original gauge length, L_0 , of 80 mm are to be tested, the values shall be the subject of agreement at the time of ordering.

Table 4: Minimum values of impact energy as determined on longitudinal V-notch test pieces

Designation		Minimum values of impact energy, in J ¹⁾ , at test temperatures, in °C, of						
Symbol as in EN 10027-1 and ECISS IC 10	Material number as in EN 10027-2	+20	0	-10	-20	-30	-40	-50
S275N S355N S420N S460N	1.0490 1.0545 1.8902 1.8901	55	47	43	40	—	—	—
S275NL S355NL S420NL S460NL	1.0491 1.0546 1.8912 1.8903	63	55	51	47	40	31	27
¹⁾ For thicknesses >100 mm for grade S460 and for thicknesses >150 mm for grades S275, S355 and S420, the values shall be the subject of agreement at the time of ordering. Option 17.								

Table 5: Minimum values of impact energy as determined on transverse V-notch test pieces (if agreed at the time of ordering)
Option 5

Designation		Minimum values of impact energy, in J ¹⁾ , at test temperatures, in °C, of						
Symbol as in EN 10027-1 and ECISS IC 10	Material number as in EN 10027-2	+20	0	-10	-20	-30	-40	-50
S275N S355N S420N S460N	1.0490 1.0545 1.8902 1.8901	31	27	24	20	—	—	—
S275NL S355NL S420NL S460NL	1.0491 1.0456 1.8912 1.8903	40	34	30	27	23	20	16
¹⁾ For thicknesses >100 mm for grade S460 and for thicknesses >150 mm for grades S275, S355 and S420, the values shall be the subject of agreement at the time of ordering. Option 17.								