

February 1995

Hexagon set screws with small hexagon,
half dog point and flat cone point

DIN
564

ICS 21 060 10

Supersedes February 1985 edition

Descriptor: Fasteners, screws, set screws

Sechskantschrauben mit Ansatzspitze und kleinem Sechskant

In keeping with current practice in standards published by the International Organization for Standardization (ISO), a comma has been used throughout as the decimal marker.

Dimensions in mm

1 Scope and field of application

This standard specifies dimensions and technical delivery conditions for coarse and fine pitch thread M6 to M36 hexagon set screws with small hexagon, half dog point and flat cone point, assigned to product grade A. These screws are only to be used as forcing screws (i.e. for adjusting and locating purposes when there is considerable resistance to motion).


NOTE: For sizes M12 and M16 screws, this standard specifies widths across flats which are in current use, i.e. 16 mm and 18 mm, in accordance with ISO 272. Specifications for obsolete widths across flats (17 mm and 19 mm) are provided in Appendix A.

Where screws are to comply with specifications other than those given in this standard (e.g. regarding nominal length or property class), these shall be selected in accordance with the relevant standards.

Continued on pages 2 to 5

Page 2 DIN 564

2 Dimensions



h (incomplete thread):
 $2 P$ max.

k_w is the minimum wrenching height; c shall be maintained within k_w .
 a_1 as in DIN 76-1. d_p , z_2 and z_3 as in DIN 78.

Table 1: Dimensions

Thread size	M6	M8	M10	M12	M16	M20	M24	M30	M36	
	—	—	—	—	—	—	M20 × 2	M24 × 2	M30 × 2	M36 × 3
$P^1)$	1	1,25	1,5	1,75	2	2,5	3	3,5	4	
a_1 max.	3	3,75	4,5	5,25	6	7,5	9	10,5	12	
d_a max.	6,8	9,2	11,2	13,7	17,7	22,4	26,4	33,4	39,4	
d_p	max. - nominal size d_p	4	5,5	7	8,5	12	15	18	23	28
	min.	3,82	5,32	6,78	8,28	11,73	14,73	17,73	22,67	27,67
e min.	8,79	11,05	14,38	17,77	19,92	26,75	33,53	39,98	51,28	
Nominal size	5	6	7	9	11	14	17	21	25	
k	min	4,85	5,85	6,82	8,82	10,79	13,79	16,79	20,74	24,74
	max	5,15	6,15	7,18	9,18	11,21	14,21	17,21	21,26	25,26
k_w min	3,4	4,1	4,8	6,2	7,6	9,7	11,8	14,5	17,3	
r min	0,25	0,4	0,4	0,6	0,6	0,8	0,8	1	1	
s	max. - nominal size s	8	10	13	16	18	24	30	36	46
	min	7,78	9,78	12,73	15,73	17,73	23,67	29,67	35,38	45,38
z_2	min. - nominal size z_2	3	4	5	6	8	10	12	15	18
	max	3,25	4,3	5,3	6,3	8,36	10,36	12,43	15,43	18,43
B_0 "	1,75	2,5	3	3,5	4,5	5	6	8	10	

¹⁾ P = pitch of thread (coarse pitch thread)

(continued)

Table 1 (concluded)

Thread size			M6	M8	M10	M12	M16	M20	M24	M30	M36
			—	—	—	—	—	M20 × 2	M24 × 2	M30 × 2	M36 × 3
<i>l</i>			Approx. mass (7.85 kg/dm ³) per 1 000 units, in kg								
Nominal size	min	max.									
12	11,65	12,35	3,93								
(14)	13,65	14,35	4,27								
16	15,65	16,35	4,61	8,30							
(18)	17,65	18,35	4,96	8,94							
20	19,58	20,42	5,32	9,54	16,5						
25	24,58	25,42	6,11	11,1	18,9	33,1					
30	29,58	30,42	7,06	12,7	21,4	36,6	60,3				
35	34,5	35,5		14,2	23,9	40,5	66,9				
40	39,5	40,5		15,8	26,4	43,8	73,5	128			
45	44,5	45,5			28,8	47,4	80,1	139	227		
50	49,5	50,5			31,3	51,0	86,6	150	243		
60	59,4	60,6				58,1	99,8	172	275	432	
70	69,4	70,6				65,3	113	194	307	479	
80	79,4	80,5					126	216	339	526	850
90	89,3	90,7					139	238	371	573	918
100	99,3	100,7						260	403	620	986
120	119,3	120,7							467	713	1 120
140	139,2	140,8								807	1 260
160	159,2	160,8								901	1 390
180	179,2	180,8									1 530
200	199,075	200,925									1 670

For the range of commercial sizes between the continuous thick lines, values of mass have been specified (for guidance only).

Bracketed sizes should be avoided if possible.

Lengths above 200 mm shall be graded in 20 mm steps.

3 Technical delivery conditions

Table 2: Technical delivery conditions

Material		Steel	Stainless steel	Nonferrous metal
General requirements		As specified in ISO 8992.		
Thread	Tolerance	6g		
	As specified in	DIN 13-15.		
Mechanical properties	Property class (material)	14H or 22H	A2-50	CuZn ¹⁾
	As specified in	ISO 898-5	ISO 3506	DIN EN 28 839.
Limit deviations and geometrical tolerances	Product grade	A		
	As specified in	ISO 4759-1.		
Surface finish		As processed. Property class 22H: (thermally or chemically) blackened. ISO 4042 shall apply with regard to electroplating. DIN 267-10 shall apply with regard to hot-dip galvanizing. DIN 267-2 shall apply with regard to surface roughness. DIN EN 26 157-3 shall apply with regard to the limits of surface discontinuities.	Bright. — — —	Bright. — — —
Acceptance inspection		As specified in ISO 3269.		
1) Copper-zinc alloy CU2 or CU3, at the manufacturer's discretion.				

4 Designation

Designation of an M8 hexagon screw with a nominal length, l , of 40 mm and assigned to property class 14H:

Hexagon screw DIN 564 – M8 × 40 – 14H

For M12 and M16 hexagon screws, widths across flats in current use, as specified in ISO 272, shall apply and are to be given in the designation, e.g.:

Designation of an M12 hexagon screw with a nominal length, l , of 60 mm, with a width across flats of 16 mm (SW 16), and assigned to property class 14H:

Hexagon screw DIN 564 – M12 × 60 – SW 16 – 14H

The screws may also be supplied with a thread undercut (Ri) conforming to DIN 962. In this case, symbol Ri shall be included in the designation, e.g.

Hexagon screw DIN 564 – M8 × 40 – Ri – 14H

DIN 962 shall apply to the designation of type and finish, with additional information to be given on ordering

The DIN 4000 - 2 - 1 tabular layout of article characteristics shall apply to the screws covered in this standard

Appendix A

Widths across flats for replacement and maintenance purposes

17 mm and 19 mm widths across flats are not included in ISO 272, and their further use is deprecated. However, should such screws be required as replacement parts, they may still be ordered with the dimensions specified in the table below. For ordering purposes, the following designation may be used (example):

Hexagon set screw DIN 564 – M12 × 60 – 14H

Table A.1: Obsolete widths across flats

Thread size	M12	M16
d_w min	18,9	21,1
max nominal size	17	19
min	16,73	18,67

Standards referred to

DIN 13-15	ISO metric screw threads; fundamental deviations and tolerances for screw threads of 1 mm diameter and larger
DIN 76-1	Thread run-outs and thread undercuts for ISO metric screw threads in accordance with the DIN 13 series
DIN 78	Thread ends and lengths of projection of bolt ends for ISO metric screw threads in accordance with the DIN 13 series
DIN 267-2	Fasteners; technical delivery conditions; product grades and tolerances
DIN 267-10	Fasteners; technical delivery conditions; hot-dip galvanized components
DIN 962	Designation system for fasteners
DIN 4000-2	Tabular layouts of article characteristics for bolts, screws and nuts
DIN EN 26 157-3	Fasteners; surface discontinuities; bolts, screws and studs for special requirements (ISO 6157-3: 1988)
DIN EN 28 839	Mechanical properties of fasteners; nonferrous metal bolts, screws, studs and nuts
ISO 272: 1982	Fasteners; hexagon products; widths across flats
ISO 898-5: 1980	Mechanical properties of fasteners; set screws and similar threaded fasteners not under tensile stresses
ISO 3269: 1988	Fasteners; acceptance inspection
ISO 3506: 1979	Corrosion-resistant stainless steel fasteners; specifications
ISO 4042: 1989	Threaded components; electroplated coatings
ISO 4759-1: 1978	Tolerances for fasteners; bolts, screws and nuts with thread diameters between 1,6 (inclusive) and 150 mm (inclusive) and product grades A, B and C
ISO 8992: 1986	Fasteners; general requirements for bolts, screws, studs and nuts

Previous editions

DIN 564: 1923-12, 1938x-12, 1951-01, 1953-06, 1983-04, 1967-12, 1985-02.

Amendments

The following amendments have been made to the February 1985 edition.

- The symbol k' has been replaced by k_w .
- For size d_p , tolerance h13 has been replaced by tolerance h13 as specified in DIN 78.
- The widths across flats have been amended for M12 and M16 screws.
- For property classes, reference is now made to ISO 898-5.
- The technical delivery conditions now also cover stainless steel and nonferrous metal screws.
- For screws with thread undercut, symbol A has been replaced by 'Ri', in accordance with DIN 962.
- The standard has been editorially revised.