UDC 621.882.215.61.091.1

May 1985

# Hexagon socket thin head cap screws with pilot recess for wrench key

<u>DIN</u> 6912

Zylinderschrauben mit Innensechskant, niedriger Kopf, mit Schlüsselführung

Supersedes December 1967 edition

In keeping with current practice in standards published by the International Organization for Standardization (ISO), a commuhas been used throughout as the decimal marker

Omensions in min

#### 1 Field of application


This standard specifies product grade A hexagon socket thin head cap screws with pilot recess for wrench key with ISO metric screw thread from M4 up to and including M36.

thin special cases, the screws are to meet requirements other than those given in this standard, e.g. with regard to property class or material, these shall be selected in accordance with the appropriate standard. This also applies to the fine pitch thread conforming to DIN 13 Part 13 required in exceptional cases.

The critical cross section of screws covered by this standard can as a consequence of the head geometry and the form of the worlds engagement be located below the hixagon socket and not in the thread. This particularly applies for fine pitch thread screws another where belearnce positions are unfavourable (see also Explanatory notes). It is thus recommended that the screws should not be used for the transmission of high axial loads involving prestressing.

These screws can not be used in the form of screw assemblies with captive washers as specified in DIN 6900, as they are always required to have a short unthreaded portion of shark to compensate for the pilot recess, taking into account strength criteria.

#### 2 Dimensions



Slight count

Slight rounding or countersink at the mouth of the socket permissible (no further than e).


u=2P maximum, incomplete thread

Bottom edge of head may be rounded or chamfered to  $d_{\rm sc}$  and shall be deburred



Top of head rounded or chamfered (pressing contour) at the manufacturer's discretion

Detail X Maximum underhead fillet



Continued on pages 2 to 7

Page 2 DIN 6912

Thread size d		ize d	- -	M 4		M 5	$\perp$	M 6	,	4 B	1	M 10		M 12	/A	A 14)	Τ.	M 16
P.2	}		-	0,7		8,0		1	1	.25		1.5		1,75		2	+	
١	5-4-	2)		14	,	6	11	B	22		2			0			+	2
	b Reference			-		_		1 -				32		6	34		38	
		4)				1		1				32			- 40		44	
,	max = nomina	dimensio	n	7	-	8.5	10		13		4						5	
$d_k$		min	-	6.78		B.28		7.78	12		16		1		21		2	4
d.,		max	- <del> </del>	4,7		5,7		5,8	9			5.73		7,73	+	0.67	2.	3.67
	min = nominal	dimension		2		2,5	3				<del></del>	.2		3.7	15		1	7,7
$d_{\mathfrak{h}}$	··	mex		2.06	<del></del>	2,56	4-1	.06	4		5			5	7			В
	usx = usumina			4		5	+			075	+	.075		5,075	7	.09	8	9.09
d,		min		3,82		.82	6		8		10		12	2	14		16	5
d,		min	+	6,2	+	.7		.82		78	9	.78	11	.73	13,	.73	15	5,73
e !)		m <sub>1</sub> n	<del></del>				+	.2	12.0		15	.03	17	7.03	19,	83	22	2,83
1				3,44 0.6	+	.58		.72	6.8		9	.15	11	.43	13,	72	16	;
<u>-</u>	nay = nominal	max.		<u> </u>	<del></del>	.6	<del></del>	.68	1,0	2	1.	.02	1	,45	1,	45	1	,45
k -	nax = nominal		-	2,8	+	.5	4		5		6.	.5	7	.5	8,	5	10	,
	·	men	+	2,66	+	,32		82	4,8	32	6,	28	7	.28	8.:	28	9	.78
	lomis -1 -1	min	<del></del>	),2		.2		25	0,4		0.	4	0	,6	0.6		0,6	
-	Nominal din	nension	3		4		5		6		8		10		12		14	
2		min	3	3,02	4.	.02	5.0	02	6.0	2	8.	025	10	.025	12.0	032		.032
	max 3,10		,10	4,12		5.	5,14		4	8.175		10,175		12,212		14,212		
-	Nominal dimension 1,6		2		2.5		3			4		4.5		5,5				
11			,48	1,88		2,38		2,88 3,35		3.85		4,35			35			
-	max 1,72		2,12		2.62		3.12 3.65		35	4,15		4.65			65			
12		ar.	3	,3	4		5		6,5		7.5		1 0		10	-	11,	
·		max	3	.6	4.	3	5.3	3	6,8	6	7,8		9.	26		+		
,		max	0.	4	0.	5	0,6	·	0.8		<u></u> 1		1,3		10,3		-11,	
	$t \rightarrow$								Shank	lengt		nd /		- 1	1,4		1.	
omina	f I		l,	$l_{\rm E}$	1.	$l_{\rm g}$	1 1,	$l_{\mu}$	1 4	/ <sub>E</sub>	1 .		1 ,	1 .	1 .			١.
ength	<u> </u>	max	win	max	min	max	min	max	mun	mak	Pun.	l <sub>E</sub>	l <sub>s</sub>	max max	I,	max	I I,	
10	9.71	10.29	1,4	3,5	1.8	4,2	2.5	5.5	-	i .		1	-		1		1	1
.12	11,65	12,35	1.4	3,5	1,8	4.2	2,5	5.5	3.2	7		7	1	† ·	÷		i	- 1
16 20	15.65	16.35	1,4	3.5	1.8	4.2	2.5	5,5	3,2	7	3.5	8	4.2	9,5	İ	†	<del>j</del>	<u> </u>
25	19.58	20.42	2.5	6		4.2		5.5	3.2	7	3.5	. 8	4.2	9.5	4.5	10.5	5	+,
30	29.58	30.42	7,5	11	5	9	2.5	5,5	3.2	7	3,5	8	4,2	9,5	4,5	10.5	5	i i
35	34.5	35.5	12.5	16 21	10	14	7	12	3.2	7	3,5	В	4.2	9,5	4,5	10.5	5	1
40	39,5	40,5	22.5	26	15	19	12	17	6.75	13	3.5	8	4.2	9,5	4,5	10,5	5	1
50	49.5	50.5	27.5	31	20 30	24	17	22	11,75	-	6.5	14	4,2	9,5	4.5	10.5	5	1
60	59.4	60,6		5.	40 1	34 44	27 37	32	21.75	28	16.5	24	11.5	20	4,5	10.5	٠.	1
70	69.4	70.6		i	10		47	42 52	31.75		26.5	34	21,5	30	16	26	12	2:
80	79.4	80.6	i i	÷			-17	3∠	41.75	48	36.5	44	31.5	40	26	36	22	32
90		90.7	1	•	1		. 1		51,75	58	46.5	54	41.5	50	36	46	32	42
00	99,3 1	007	- !				· i			.	56,5	64	51.5	60	46	56	42	52
10)	109,3 1	10,7	•		÷	i	:						61,5	70	56	66	52	62
20		20,7			:										66	76	62	72
		30.8	ï	1	į	1	į		1		i	j	.		76	86	72	82
40	139,2 1	40,8			i	!	!				:	i	!			- ;	76	86
$P_{B}$	jutch of in	nead (co	oarse	pitchie	hread)						-		1				86 i	96
1 (3)	rengths ( -	-125 mi	11															
101	lengths $I$ lengths $I$	<ul> <li>200 me</li> </ul>	u - 20 n	io mini														
	)/) = 1.14 .																	

Fax:062084389 Aug 15 2001 16:43 P.03/07

DIN 6912 Page 3

	Thread s	nze d	- (	M 18)		A 20	(N	122)	I	M 24		(M 2	7)	M 30		M 33	1 i	M 36	
P 9				2.5	1.	2.5	2	2.5		3		.3	+	3,5	- !	3,5	<del></del>	4	
1.0		'n		12	. 4	6	50	)	-	54		60	* **	66	ı	72		78	
	eference mension	')	4	18	5	2	56	i	1 (	i()	•	66		72		7H	1	84	
		13	6	÷1	6	65				7:3	•	79	ı	85		) 1	i	97	
, 6	пах — поти	al denense	n   2	27	3	)	33		1 :	36	i	40	:	45		iO			
$d_{\mathbf{k}}$		ettiet	2	6.67	2	1,67	32	:61	1.	15,61		39.61	;	44.61			i	54	
$d_{+}$		-7.44	] 2	0.2	. 2	2.4	24	4		26.4		30,4		33,4		19,61		53.54	
	no = moma	al dimension	, [	8	10	)	1 10			2	•	12				36 4		39,4	
d <sub>h</sub>		775.44	1	8.09	-1	0.09	•	.09		2,11				15		6.5		113	
,,	лах жистип	af dimensio	, l	8	20		22		•	24		12.11		15, t I		6,61		18,11	
d,		22-21	4 .	7.73	+	67	21		1			27		30		3.3	:	.36	
$d_{\infty}$		211471	1	5.83	i -	1.83	31		٠	3.67		26,67		29,67		12,61		35,61	
(		mio	1	6		.44	1			4.61		38,61		43.61		8,61	i	52,34	
;'			1 .	1.87	4		19.			1,73	i	21,73		25,15	. 2	7,43	1	30.85	
' :	131 = nome	max al dunionsino	1		1	.04		04	:	2.04		2.89		2.89		2.89		2.89	
k	ax =nomin		· F		12		; 13			-1		lá .		17,5	1	9.5	:	21.5	
		inui	1	0,73	:	.73	! 12.			3,73		15.73		17,23	1	9,17	1	21,17	
		min		0.6		.8	0,	8	l	8.0		1 .		1	•	1	•	1	
_	ominal d	mension	1		; 17		17		11	9		19	. :	22	2	4	- 1 -	27	
N		Ann.	14	4.032	. 17	.05	177	05	. 19	9.065		19.065		22.065	2	4.065	Ť-	27.065	
		max	1.	1,212	1.7	17.23		17.23		9,275	19,275		5 2	22.275		24.275		27,275	
N	ominal di	mension	- 6	3	6.5		7	7		7 8.5			9		10		11.5		
1,	fs min			5.85	6.32		6,82			6.82 8.32			8.82		9.82		11,28		
	max			3.15	, 6	68	7.	18		7,18	- i	8.68		9.18		0.18		11.72	
		min	12	2,5	14		15		16			17		9	20				
$t_2$		max	12	2,93	14,	43	15,	13	t	3,43	-:	17,43		9.52	******	 0.52		24	
v.		max	1	,8	2		2.3	2	•	2.4		2.7		3.32				24.52	
	l						-		ــــــــــــــــــــــــــــــــــــــ		othe	I, and	<del>,  </del>		<u>'</u> ,	3.3		3,6	
Neminai	1	1	1	1/4	I,	$I_{\mu}$	1.	$l_{\mu}$	1 4	/ /K	L				; ,				
length	min	тая	min	max	min	max	min	max	min	max	min	l <sub>k</sub>	- Ti	l <sub>u</sub> max	l, I min	l <sub>k</sub>	l,	l <sub>x</sub>	
20	19,58	20,42		II				i	Ī		i			╁	<del> </del>		1		
25	24,58	25,42	5,5	13						-		†		†	<del> </del> -	-	<del> </del>	<del> </del> -	
30	29.58	30,42	5.5	13	6,5	14		Ĺ	i	1	i	-		1	<u> </u>	!		<del> </del>	
35	34.5	35,5	5.5	13	6.5	14				I	i.			$\vdash$	l	1	† <del></del>		
40	39.5	40.5	5,5	13	6.5	14	6.5	14									i	†	
50 60	49.5	50.5	5.5	13	6.5	14	6,5	14									<u> </u>	Γ	
70	59.4 69.4	60.6 70.6	5,5	13	6.5	14	6.5	14	. 7	16									
80	79.4	80.6	15,5 25,5	28	21.5	24 34 l	6,5	14	7	16	. 8	17	8,5	19			ļ		
90	89,3	90.7	35.5	48	31.5	44	17.5 27.5	30	21	16	8	17	8.5	19	9.5				
100	99.3	100.7	45.5	58	41,5	54	37.5	40 50	31	36 46	8		8.5		9.5	20	10.5	22.5	
(110)	109.3	110.7	55.5	68	51.5	641	47.5	- 60	41	56	25	40 50	8.5	19	9.5	20	10.5	22.5	
120	119.3	120.7	65.5	78	61.5	74	57,5	70	51	: 66:	45	60	26.5 36.5	54	9,5	20 48		22,5	
(130)	129.2	130,8	69,5	82	65.5	78	61.5	74	55	70	49	64	40.5	58	34.5	52	10.5	22,5 46	
140	139,2	140.8	79.5	92	75.5	88	71.5	84	65	80	59	74	50.5	68	44.5	62	36	46 56	
150)	149,2	150,8	89.5	102	85.5	98	81,5	94	75	90	69	84	60.5	78	51.5	72	46	66	
160	159.2	160.8	1		95.5	108	91.5	104	85	100	79	94	70.5	88	64.5	82	56	76	
170)	169.2	170.8			105.5	118	101.5	114	95	110	89	104	80.5	98	74.5	92	66	86	
180	179.8	8.081			115.5	128	111.5	124	105	120	99	114	90.5	108	818	102	76	96	
190)	189.1	190,9				1	121,5	134	115	130	109	124	100,5	118	94.5	112	86	106	
200	199,1	200,9				<u> </u>	131,5	144	125	140	119	134	110,5	129	104.5	122	96	116	
00.00	ge 2 for 1	) to 5)					_												

Fax:062084389

Aug 15 2001 16:44

P. 04/07

#### Page 4 DIN 6912

The commercial nominal lengths are designated by giving the shank lengths,

The thread sizes and intermediate lengths given in brackets shall be avoided where possible

Nominal lengths above 200 mm shall be graded by steps of 20 mm.

The distance from the last full form thread to the head bearing surface shall be  $I_p$  max  $\approx 5P$  for bolts with nominal lengths above the dashed stepped line. The  $I_p$  and  $I_p$  values for bolts with nominal lengths below the dashed stepped line shall be determined in accordance with the following equations

 $I_{\rm g}$  max. = I (nominal length) – h (nominal length),  $I_{\rm s}$  min =  $I_{\rm g}$  max. = 5 P.

# 3 Technical delivery conditions

Mai	terial	Steel	Stainless steel	Nonferrous metal				
General requireme	ents	As specified in DIN 267 Part 1.						
Thread	Tolerance class	6 g						
illeau	Standard		DIN 13 Part 12 and Part 15	5				
Mechanical	Property class (material)	8.8	≤ M 20: A2-70; > M 20: A2-50.	CuZn = copper-zinc alloy?)				
properties		Other property classes or materials subject to agreement.						
	Standard	ISO 898 Part 11)	DIN 267 Part 11	DIN 267 Part 18				
Permissible dimensional deviations and	Product grade	A						
deviations of form	Standard	ISO 4759 Part 1						
		(Thermally or chemically) blackened	Bright.	Bright.				
Surface finish		DIN 267 Part 2 shall apply with regard to the surface roughness.  DIN 267 Part 19 shall apply with regard to the permissible surface discontinuities.  DIN 267 Part 9 shall apply with regard to electroplating.  If a different kind of electroplating or a different kind of surface protection is desired, this shall be agreed upon at the time of ordering.						
Acceptance inspect	lion	DIN 267 Part 5 shall apply with regard to acceptance inspection.						

The acceptance inspection shall include hardness testing of property class 8.8 screws, with hardness values of HV 250 to 320 for sizes up to and including M 16, and HV 255 to 335 for sizes greater than M 16 (see Explanatory notes).

# 4 Designation

Designation of an M12 hexagon socket head cap screw of nominal length  $I = 60 \, \text{nm}$  and assigned to properly class 8.8 Hexagon socket head cap screw DIN 6912 - M 12  $\times$  60 - 8.8

OIN 962 shall apply with regard to the designation of types and designs with additional information to be given on ordering. The DIN 4000-2-1 tabular layout of article characteristics shall apply for screws covered by this standard.

Preferably CU2 or CU3, at the manufacturer's discretion.

Fax:062084389

Aug 15 2001 16:44 P.05/07

DIN 6912 Page 5

### 5 Masses

Thread size if	M 4	M 5	М 6	MB	M 10	M 12	(M 14)	MIG			
Nominal length /	Mass (7,85 kg/dm³), in kg per 1000 units $\sim$										
10	1,3	2.2	3,6	1	!	i	T				
12	1.5	2.5	3,9	7 7	Ì	İ		}			
16	1,9	3,1	4.5	8.8	15,5	22,3	1				
20	2,3	3.7	5.2	10.2	17.9	25,5	37,9	52,			
25	2,7	4.4	6.2	12.5	20.2	29.5	42.5	56.			
30	3.2	5,1	7.3	14	22	32,5	48	63			
35	3,4	5,8	8,3	15,7	25,5	36,5	53	69.			
40	4.2	6,6	9,5	17.5	28.5	40	58	78,			
50	5.2	7.3	11,5	21,5	34.8	48	69.5	91.5			
60		9	13,6	25.3	40,3	57	82	107			
70			15,7	29.1	46	65	92,5	122			
80				32,8	52,5	72	104	140			
90			İ	; [	57.8	80	116	154			
100						88	127	169			
110			1		1		139	183			
120			i		,	- 1	151	198			
130								212			
140								226			

Thread size il	(M 18)	M 20	(M 22)	M 24	(M 27)	M 30	(M 33)	M 36			
Nominal length I	Mass (7,85 kg/dm <sup>3</sup> ), in kg per 1000 units ≈										
20		1				i	<del></del>	Γ			
25	77						ļ				
30	84,6	108									
35	93,3	118									
40	102	128	185				ļ ··· · ·				
50	119	150	215								
60	138	172	245	263				-			
70	157	196	275	298	445	498					
80	178	222	305	333	490	552	793				
90	196	245	335	369	535	607	860	1000			
100	215	269	365	407	580	662	927	1080			
110	235	292	395	439	625	717	994	1160			
120	255	316	425	474	670	772	1060	1240			
130	275	342	455	510	715	827	1130	1320			
140	295	368	485	545	760	880	1190	1400			
150	315	394	515	580	805	940	1250	1470			
160	į	422	545	616	850	990	1320	1550			
170		448	575	651	895	1050	1380	1630			
180		474	605	687	940	1100	1450	1710			
190			635	722	995	1160	1510	1790			
200			665	758	1030	1210	1580	1870			

The values of mass specified for the commercial sizes are for guidance only.

Fax:062084389

Aug 15 2001 16:45

P.06/07

Page 6 DIN 6912

Standards	referred	to
-----------	----------	----

		ined to
DIN	13 Part 12	ISO metric screw threads, coarse and fine pitch threads from t to 300 mm diameter; selection of diameters and pitches.
DIN	13 Part 13	ISO metric screw threads, selected sizes for screws, holts and nuts from 1 to 52 mm screw thread diameter and limits of size.
DIN	13 Part 15	$ISO\ metric\ screw \ threads, fundamental\ deviations\ and\ tolerances\ for\ screw\ threads\ of\ t\ mm\ diameter\ and\ larger$
DIN	78	Thread ends and lengths of projection of bolt ends for ISO metric threads in accordance with DIN 13
DIII	267 Part 1	Fasteners, technical delivery conditions, general requirements
DIM	267 Part 2	Fasteners; technical delivery conditions; types of finish and dimensional accuracy
1)114	267 Part 5	Fasteners, technical delivery conditions, acceptance inspection
DitA	267 Part 9	Fasteners; technical delivery conditions, electroplated components
DIM	267 Part 11	Fasteners, technical delivery conditions with addendato ISO 3506; stainless and acid resistant steel components
DIN	267 Part 18	Fasteners; technical delivery conditions, nonferrous metal components
DIM	267 Part 19	Fasteners; technical delivery conditions; surface discontinuities on bolts
DIN	962	Bults, screws, studs and nuts, designations, types and finishes
DIN 4	1000 Part 2	Tabular layout of article characteristics for bolts, screws and nuts
DIN 6	900	Screw assemblies
ISO	898 Part 1	Mechanical properties of fasteners, bolts, screws and studs
ISO 4	1759 Part 1	Tolerances for fasteners, bolts, screws and nuts with thread diameters $\geq$ 1,6 and $\leq$ 150 mm and product grades A, B and C

#### Previous editions

DIN 6912: 03.54x, 12.67

#### Amendments

The following amendments have been made in comparison with the December 1967 edition:

- a) The content of the standard has been editorially revised and harmonized with DIN 912.
- b) Screws with fine pitch thread have been deleted
- c) Shank lengths have been specified (see Explanatory notes).
- d) The head bearing surface has been dimensioned in detail (see Explanatory notes).
- e) The technical delivery conditions have been supplemented and harmonized with the corresponding basic standards
- I) Design m has been replaced by product grade A
- g). Maximum and minimum values have been adopted for the individual dimensions
- h). The hardness test has been specified as the determining test for the acceptance inspection.

# **Explanatory notes**

Relamendment at

In respect of its dimensional specifications and its layout, Standard DIN 912, December 1983 edition, corresponds to International Standard ISO 4762 - 1977. The national amendments and/or supplements required have been identified. The same layout has been selected for this standard, DIN 6912, and the other standards covering hexagon socket screws, DIN 7984 and DRI 7981, although, at present, no international standards comparable to these standards have yet been published.

He amendment by

Cap is rews conforming to DIN 6912 are only seldom required with fine pitch thread. This thread has been deleted from the standard for this reason. However, according to the field of application, screws with fine pitch thread may continue to be ordered in accordance with this standard, if required.

Re amendment of

As an addition to the previous specifications, dimensions have been specified for the shank lengths  $(l_i$  and  $l_j$ )  $l_k$  can be considered to represent the minimum graphength. Thread length h, which has remained unamended at  $2 \times d + 6$  mm or  $2 \times d + 12$  or  $2 \times mn$  is mow only applicable as reference dimension for calculating  $l_j$  and  $l_i$ . This dimension also covers the tolerance on the nominal length l and the previous tolerance on thread length  $l_i$  at the thread runout A value corresponding to  $i \in SP$  has been inserted for the dimension  $l_i$  of screws with a nominal height above the disshed stepped line, so that the thread does not extend too far into the area of the plot recess (which would result in a weakening of the cross section). This corresponds approximately to the previous specifications given in DIN 0912 (timpersion  $l_i$  min.). There is no risk to interchangeability as a consequence of the amended dimensioning

## DIN6912-85 (1728x2274x2 tiff) [7]

Fax:062084389

Aug 15 2001 16:45

P.07/07

DIN 6912 Page 7

### Re amendment d)

The head bearing surface and the underhead fillet of the screw have been dimensioned in detail by analogy with DIN 912. As a deviation from DIN 912, a minimum bearing surface diameter corresponding to  $d_{\infty}$  min. =  $d_{\infty}$  min. = IT 15 has been specified for sizes up to M 24, following proper cold forming practice (see also Explanatory notes to DIN 912 in this respect).

Re amendment h)

As it is possible for the critical cross section in these screws to lie heliween the hexagon socket and the shank, they are excluded from the wedge loading test (see ISO 898 Part 1, April 1979 edition, table 5). Furthermore, according to a revision agreed in October 1984 by Subcommittee SCT of Technical Committee ISO/TC 2, the hardness test has been made mandatory for acceptance inspection as specified in ISO 898 Part 1, table 3. In addition to revised hardness values, this specifies that screws having a head style which is (or could be) weaker than the threaded portion, shall be inspected by means of hardness testing.

# International Patent Classification

F 168 23/00